

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
5 December 2002 (05.12.2002)

PCT

(10) International Publication Number  
**WO 02/096255 A1**

(51) International Patent Classification: **A47K**

Appleton, WI 54914 (US). **HUANG, Yung, Hsiang**; 2420 West Seneca Drive, Appleton, WI 54914 (US).

(21) International Application Number: PCT/US02/16996

(22) International Filing Date: 31 May 2002 (31.05.2002)

(74) Agents: **BENDEL, Michael, J.** et al.; **KIMBERLY-CLARK WORLDWIDE, INC.**, 401 N. Lake Street, Neenah, WI 54956 (US).

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

09/871,020	31 May 2001 (31.05.2001)	US
09/871,019	31 May 2001 (31.05.2001)	US
10/161,166	30 May 2002 (30.05.2002)	US

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW.


(71) Applicant: **KIMBERLY-CLARK WORLDWIDE, INC.** [US/US]; 401 N. Lake Street, Neenah, WI 54956 (US).

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors: **SOSALLA, Gerald, Keith**; 340 West Prospect Avenue, Appleton, WI 54911 (US). **AMUNDSON, John, David**; 72 Lyon Close, Maidenbower, Crawley, Sussex RH10 7NE (GB). **KUO, Andrew**; 2340 Skylark Drive,

[Continued on next page]

(54) Title: **STACK OF FAN FOLDED MATERIAL AND COMBINATIONS THEREOF**



(57) Abstract: The invention relates to a stack of fan folded material and related systems and processes. The stack includes at least two clips of fan folded material. Each clip includes a plurality of fan folded sheets, with each sheet joined to at least one adjacent sheet by a weakened line. Each clip is joined to an adjacent clip by a last sheet of one clip being separably joined to a first sheet of a succeeding clip.

WO 02/096255 A1

**Declarations under Rule 4.17:**

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

## STACK OF FAN FOLDED MATERIAL AND COMBINATIONS THEREOF

BACKGROUND OF THE INVENTION

Wiping sheets or wipes have been made from a variety of materials which can be dry or wet when used. Wipes can be moistened with a variety of suitable wiping solutions, and are then usually referred to as wet wipes. Typically, wipes have been stacked in a container in either a folded or unfolded configuration. For example, containers of wet  
5 wipes have been available wherein each of the wet wipes stacked in the container has been arranged in a folded configuration such as a c-folded, z-folded or quarter-folded configuration as are well known to those skilled in the art. Sometimes the folded wet wipes have also been interfolded with the wet wipes immediately above and below in the stack of wet wipes. In yet other configurations, the wipes have been placed in the  
10 container in the form of a continuous web of material of similarly weakened line connected sheets from the first sheet to the last which includes perforations to separate the individual wipes and which wipes can be stacked on top of each in a fan folded manner or wound into a roll. Such wipes and wet wipes have been used for baby wipes, hand wipes, household cleaning wipes, industrial wipes and the like.

15 The conventional packages which contain wipes, such as those described above, have typically been designed to be positioned on a flat surface such as a countertop, changing table or the like. Such conventional packages have generally provided a plastic container, tub or package which provides a sealed environment for the sheets or wipes to ensure that they do not get contaminated by the environment surrounding the container or  
20 become overly dry in the case of wet wipes. Some of the conventional packages have also been configured to provide one at a time dispensing of each wipe which can be accomplished using a single hand after the package has been opened. Such single handed, one at a time dispensing, often referred to as "pop-up" dispensing, is particularly desirable because the other hand of the user or care giver is typically required to be  
25 simultaneously used for other functions. For example, when changing a diaper product on an infant, the care giver typically uses one hand to hold and maintain the infant in a desired position while the other hand is attempting to dispense a wet wipe to clean the infant.

30 However, the dispensing of wipes from such conventional containers for wipes has not been completely satisfactory. For example, this is due at least in part to the configuration of the wipes within the container. In particular, for example, this concerns the relationship of each wipe in the container to each adjacent wipe in the container, such

as a stack of wipes. As another example, this can concern the relationship of a group of wipes in the stack to other wipes in the stack if groups of wipes make up the stack of wipes. As yet another example, these relationships between wipes concern, in conjunction with the wipes, the container from which the wipes are dispensed and  
5 characteristics thereof.

### SUMMARY OF THE INVENTION

In response to the difficulties and problems discussed above, for example, a new  
10 relationship between two adjacent sheets or wipes, as well as between groups of sheets, enabling improved dispensing, and which may be more cost effective and reliable (e.g., reducing the likelihood of wipe fallback and/or reducing the likelihood of multiple wipes dispensing undesirably), has been discovered. For example, dispensing can be improved or made easier when a wipe is ready for dispensing upon the opening of a resealable  
15 wipes dispenser after the initial opening of the dispenser and use of a first wipe in a plurality of wipes. That is, a portion of the wipe is positioned in an orifice of the dispenser sufficiently protruding so a user can readily grasp the same and remove the entire individual wipe without premature tearing or non-dispensing of the top wipe. As another example, "wipe fallback" can occur when a leading wipe in a plurality of wipes separates  
20 completely from a following or trailing wipe prematurely, i.e., before a sufficient portion of the following wipe is positioned within the dispenser orifice to remain there for later dispensing after the leading wipe is fully separated or disjointed from the trailing wipe outside the dispenser. In such a fallback situation, the following wipe would need to be re-threaded through the dispensing orifice when its dispensing is next desired. This may  
25 not be undesirable if done intentionally, i.e., if maintaining a maximum moisture level for the sheets is desired, e.g., for wet wipes, and if the dispensing orifice is designed to easily accommodate reach-in retrieval of the next sheet. As yet another example, "multiple wipes" dispensing can occur when a leading individual wipe in a plurality of wipes does not timely separate completely from a following individual wipe while the following wipe is  
30 still at least partially maintained in the dispensing orifice, i.e., the following wipe dispenses completely out of the dispenser with the leading wipe causing two (or more) wipes to dispense substantially simultaneously. This can be desirable when two (or more) wipes are needed, but if only one is desired, then this is not preferred.

The purposes and features of the present invention will be set forth in and are  
35 apparent from the description that follows, as well as will be learned by practice of the invention. Additional features of the invention will be realized and attained by the product

and processes particularly pointed out in the written description and claims hereof, as well as from the appended drawings.

In one aspect, the invention provides a stack of fan folded material. The stack includes at least two clips of fan folded material. Each clip includes a plurality of fan  
5 folded sheets, with each sheet joined to at least one adjacent sheet by a weakened line. Each clip is joined to an adjacent clip by a sheet of one clip being separably joined (e.g., by adhesive or interfolding) to a sheet of a succeeding clip.

In another aspect, the invention provides a stack of fan folded material. The stack includes at least two clips of fan folded material. Each clip includes a plurality of fan  
10 folded sheets which can be folded along a machine direction of the sheets, with each sheet joined to at least one adjacent sheet by a weakened line which can also be formed in the machine direction of the sheets. Each clip is joined to an adjacent clip by a last sheet of one clip being adhesively joined to or interfolded with a first sheet of a succeeding clip.

15 In other aspects, the invention provides a process for forming a stack of fan folded material. This can include various steps and in various orders or as follows: providing an elongate web of material; weakening the elongate web of material along a plurality of lines to form a plurality of panels joined to adjacent panels along the plurality of lines; folding the plurality of panels together; cutting the plurality of panels to form a plurality of clips;  
20 and joining each clip to an adjacent clip by separably joining a bottom portion of one clip to a top portion of a succeeding clip.

In still other aspects, the invention provides a stack of fan folded material. The stack includes at least two clips of fan folded material. Each clip includes a plurality of fan folded sheets, with each sheet joined to at least one adjacent sheet by a weakened line.  
25 Each clip is joined to an adjacent clip by a sheet of one clip being separably joined to a different sheet of a succeeding clip.

In another aspect, the invention provides an alternate process for forming a stack of fan folded material. This can include various steps and in various orders or as follows: (a) providing an elongate web of material; (b) weakening the elongate web of material along a  
30 plurality of lines to form a plurality of panels joined to adjacent panels along the plurality of lines; (c) folding the plurality of panels together to form a first ribbon of panels; (d) repeating steps (a) to (c) for at least a second elongate web of material and thereby forming at least one succeeding ribbon of panels; and, (e) joining the first ribbon to the succeeding ribbon by separably joining a top portion of the first ribbon to a bottom portion  
35 of the succeeding ribbon to form a ribbon stack. Additionally, this can include cutting the ribbon stack to form a plurality of clips of fan folded material.

In yet other aspects, the invention provides a dispensing system for fan folded material. The system includes a dispenser having a base and a top enclosing an interior. A stack of fan folded material can be stored in the interior, with the top including an opening through which the fan folded material can pass to an external position outside the dispenser. The stack of fan folded material includes at least two clips of fan folded material. Each clip includes a plurality of fan folded sheets, with each sheet joined to at least one adjacent sheet by a weakened line. Each clip is joined to an adjacent clip by a last sheet of one clip being separably joined to a first sheet of a succeeding clip.

In still other aspects, the invention provides a dispensing system for fan folded material. The system includes a dispenser including a base and a top enclosing an interior. A stack of fan folded material is stored in the interior, with the top including an opening through which the fan folded material can pass to an external position outside the dispenser. The stack of fan folded material includes at least two clips of fan folded material. Each clip includes a plurality of fan folded sheets, with each sheet joined to at least one adjacent sheet by a weakened line. Each clip is joined to an adjacent clip by a sheet of one clip being separably joined to a different sheet of a succeeding clip.

In still further aspects, the invention provides a process for dispensing a stack of fan folded material from a dispenser. This can include various steps and in various orders or as follows: pulling a first sheet of the material through an opening of the dispenser; separating the first sheet from a subsequent adjacent second sheet of the material at a weakened line between the first and second sheets; pulling a subsequent third sheet of the material through the opening of the dispenser; and separating the subsequent third sheet of the material from a subsequent adjacent fourth sheet of the material at a separably joined interface between the third and fourth sheets, wherein the separably joined interface between the third and fourth sheets is a different type of separably joined interface from the weakened line between the first and second sheets.

In yet further aspects, the invention provides a process for dispensing a stack of fan folded material from a dispenser. This can include various steps and in various orders or as follows: pulling a first sheet of the material through an opening of the dispenser; separating the first sheet from a subsequent adjacent second sheet of the material at a first type of separably joined interface between the first and second sheets; pulling a subsequent third sheet of the material through the opening of the dispenser; and separating the subsequent third sheet of the material from a subsequent adjacent fourth sheet of the material at a second type of separably joined interface between the third and fourth sheets wherein the second type of separably joined interface is a different type of separably joined interface from the first type of separably joined interface.

In yet other aspects, the invention provides various configurations for the weakened line, the wipes per se, and the wipes relative to other wipes such as in a stack of wipes.

In still other aspects, the invention is provided for use in various types of dispensers and for dispensing in various manners such as reach-in dispensing and pop-up dispensing.

As used herein, the term "machine direction" or MD means the length of a fabric or material in the direction in which it is being converted. The term "cross machine direction" or CD means the width of fabric, i.e. a direction generally perpendicular to the MD.

As used herein, sheets of the invention are considered "separably joined", "separably joining" (and variations thereof) when each sheet of a plurality, e.g., in a stack of sheets, is engaging any adjacent sheet while in the dispenser or package such that withdrawing the leading sheet through the dispenser or package opening also withdraws at least a portion of the following sheet through the opening before the leading sheet and the following sheet separate completely from each other. Such engaging of any adjacent sheet can include an interfolded relationship or a non-interfolded relationship in combination with one or more of the following between adjacent sheets: adhesive, friction, cohesion, fusion bonding (e.g., ultrasonic welding, heat sealing), mechanical entanglement (e.g., needle punching, steam sealing, embossing, crimping), autogeneous bonding, and/or weakened line(s) (e.g., perforations, zones of frangibility, score line(s), crush cutting).

As used herein, when the following sheet that has at least a portion through the opening of the dispenser or package is intentionally maintained in the opening after the leading sheet is completely separated from the following sheet, this is referred to as "pop-up" format or dispensing. To be intentionally maintained in the opening means the opening is configured to so maintain the sheet therein, such as through use of a constricting opening or opening being smaller than the sheet in at least one dimension of the sheet.

As used herein, "reach-in" dispensing is understood to mean having to fetch a wipe out of a container through an opening substantially co-extensive with the walls of the container or through a restricted opening smaller than the perimeter defined by the walls. In either case, the top wipe for dispensing rests on top of the remainder of the stack of wipes and the top wipe needs to be separated from the remainder of the stack each time anew when dispensing is desired. An example of a reach-in dispenser is found in the currently available baby wipes product sold by Kimberly-Clark Corporation of Neenah, Wisconsin under the trade name HUGGIES® Supreme Care.

It is to be understood that both the foregoing general description and the following detailed description are exemplary and are intended to provide further explanation of the invention claimed. The accompanying drawings, which are incorporated in and constitute part of this specification, are included to illustrate and provide a further understanding of the wiper of the invention. Together with the description, the drawings serve to explain the various aspects of the invention.

### BRIEF DESCRIPTION OF THE DRAWINGS

The present invention will be more fully understood and further features will become apparent when reference is made to the following detailed description of the invention and the accompanying drawings. The drawings are merely representative and are not intended to limit the scope of the claims. Like parts depicted in the drawings are referred to by the same reference numerals.

**Figure 1** representatively shows a schematic view of an apparatus and process for forming a stack of fan folded material, in accordance with the present invention.

**Figure 1A** representatively shows a cross sectional view of a portion of the apparatus of Figure 1, taken along the line A-A.

**Figure 2** representatively shows a front view of a portion of an arched roller assembly and folding assembly for use with the present invention, similar to that seen in Figure 1.

**Figure 2A** representatively shows an enlarged side view of a portion of the arched roller assembly and folding assembly taken along the line A-A of Figure 2.

**Figure 2B** representatively shows an enlarged front view of a portion of the folding assembly taken along the line B-B of Figure 2A.

**Figures 3, 3B, 3C and 4** representatively show schematic side views of clips of fan folded sheets, in accordance with the present invention.

**Figures 3A and 4A** representatively show schematic top views of a portion of the sheets of Figures 3 and 4, respectively.

**Figure 5** representatively shows a side view of a pair of shear slitters for use with the present invention.

**Figure 5A** representatively shows an edge view of the pair of shear slitters in Figure 5.

**Figure 6** representatively shows a partial cross-sectional view of a roller journal unit for use with the present invention.



**Figure 6A** representatively shows a side view of the journal shaft of Figure 6, but with the view rotated about the longitudinal axis 90 degrees.

**Figure 6B** representatively shows an end view of a pair of journal shafts like that seen in Figure 6, but here as they would be joined together in the arched roller assembly.

5        **Figure 7** representatively shows an end view of a folding board for use with the present invention.

**Figure 7A** representatively shows a bottom view of the folding board of Figure 7.

**Figure 8** representatively shows a side view of an alternate folding board for use with the present invention.

10       **Figure 8A** representatively shows an end view of the folding board of Figure 8.

**Figure 9** representatively shows a schematic diagram for making sheets, e.g., wet wipes, in accordance with the present invention.

**Figure 10** representatively shows a schematic diagram for alternately making sheets, in accordance with the present invention.

15       **Figure 11** representatively shows a perspective view of a type of non-rigid dispenser for use with wipes of the present invention, where wipes are sealed therein and the dispenser is sealed closed.

**Figure 12** representatively shows a perspective view of the dispenser of Figure 11, where a wipe is ready for pop-up dispensing and the dispenser is open.

20       **Figure 13** representatively shows a perspective view of a type of rigid dispenser for use with wipes of the present invention, where wipes are sealed therein and the dispenser top is open.

**Figure 14A** representatively shows a schematic side view for wipes about to be adhesively joined together, in accordance with the present invention.

25       **Figure 14B** representatively shows a partial cross sectional expanded side view of the wipes of Figure 14A, now adhesively joined together and in a position separating one wipe from the other.

**Figure 15A** representatively shows a schematic side view of wipes about to be adhesively joined together, in accordance with the present invention.

30       **Figure 15B** representatively shows a partial cross sectional expanded side view of the wipes of Figure 15A, now adhesively joined together and in a position separating one wipe from the other.

**Figure 16** representatively shows a perspective view of a test machine with the two wipes of Figures 14A or 15A positioned therein before the machine is activated.

**Figure 17** representatively shows a perspective view of the test machine and wipes of **Figure 16** while the machine is activated and as the wipes become partially disjointed from each other.

**Figure 18** representatively shows a combined partial side view and schematic view of an alternate apparatus and process for forming a stack of fan folded material, in accordance with the present invention.

### DETAILED DESCRIPTION OF THE INVENTION

As representatively illustrated throughout the figures, and for explanation now referring to **Figures 1 to 2B**, inclusive, there is depicted an apparatus and process for making a stack 10 of fan folded material. Starting on the right side of **Figure 1**, there is a roll 30 of basesheet material 31. The roll can be supported by a roll support 33. The material is fed from the roll 30 through a series of advancing rollers such as idler rollers 32 and dancer roller 34. From there the web of material 31 travels to a slitter assembly 40. The slitter assembly can include an anvil roller 42 and slitting blades 44 that form weakened lines 24 (e.g., perforated slitting blades that thereby form perforations 25) in the sheet as it travels in the machine direction 38 through the slitting assembly. As a result of traveling through the slitting assembly, the web is formed into a plurality of panels 28 joined to adjacent panels along the plurality of weakened lines 24. From there the sheet travels over an upper idler roller 46 and over to an arched roller assembly 50. The web then travels into the folding assembly 60. The folding assembly includes a series of folding boards 62 that assist in necking down the web in the cross direction 39 in a controlled fashion to induce machine direction 38 folds.

As the web travels down the folding assembly 60, it can encounter a moistening assembly 70. Assembly 70 can include a bar 72 having ports 74 for imparting liquid or solution onto the moving web as it is necked down into a fan folded ribbon of material. A liquid or solution can be provided at a desired add-on rate and in a conventional manner to the bar 72 so it can be applied through ports 74 to the moving web. Such application could include spraying or drooling with a bar like 72, or could include alternate structures (not shown) for techniques such as printing, a bath, a flooded nip, or hollowed out folding boards with spray orifices that project fluid in a rather even horizontal plane as the web moves by the boards. Alternatively, if a dry final product is desired the moistening assembly can be eliminated and otherwise the manufacturing apparatus and process could be the same. As the web travels further down the folding assembly, the sheet becomes corrugated to a point where the web is compressed in the cross direction by

means of nip rollers 76. At this point, the web forms a single ribbon of fan folded sheets that then travels by a conveyor assembly 80 including a pull roller 82, support belt 84 and support rollers 86 which are an idler roller and a drive roller. The web continues travel to an adhesive application assembly 90. The adhesive assembly applies adhesive 92 via an adhesive nozzle 96 to the top of the ribbon, e.g., along an edge. Adhesive can be applied by various techniques known to those of skill in the art. For example, when the sheets comprise wet wipes, some such ways are described in a U.S. patent application filed separately but concurrently herewith entitled, "PROCESS FOR JOINING WET WIPES TOGETHER AND PRODUCT MADE THEREBY" of inventors Yung H. Huang et al., U.S. Serial No. 09/870815, assigned to the same assignee of this application and known by attorney docket number 15,991, which application is incorporated herein by reference.

The ribbon with adhesive applied thereto travels on to a cutter assembly 100, which includes a rotary cutter 102 and anvil roller 104. The ribbon is then cut into discreet pieces, called clips 20, which then pass to a stacker assembly 110. The stacker assembly includes a stacker belt 112 and stacker rollers 114 which are an idler roller and a drive roller. In the stacker assembly 110, the clips 20 are stacked one upon the other and thereby the adhesive 92 on the top sheet of a clip adheres to a bottom sheet of the subsequent clip that is stacked on top of it. A desired number of clips are stacked one on top of another and adhesively joined in this manner. An example of such an apparatus for use as the stacker assembly is provided with a variety of conventional wet wipe machines sold by Paper Converting Machine Company of 2300 S. Ashland Ave., Green Bay, Wisconsin 54307, under the tradename Triton™ Wet Wipes Machine. Other stackers that could be employed are those supplied with a ZFV™ folder, sold by Elsner Engineering of Hanover, Pennsylvania USA or a Serv-O-Tec™ folder sold by Serv-O-Tec in Lagenfeld Germany (Serv-O-Tec is a division of Bretting Mfg. in Ashland WI, USA). Then, the completed stack is moved to a packaging assembly (not shown) where the clips can be put in various types of dispensers (e.g., tubs, bags, etc.) and then made ready for commercial sale and use.

Generally, and referring to **Figures 3 to 4A**, inclusive, the invention relates to a stack 10 of at least two clips 20 where each clip comprises at least two sheets 22 separably joined together along a weakened line 24. Each clip 20 is separably joined to an adjacent clip, e.g., advantageously by the last sheet 22a of one clip being joined to the first sheet 22b of a succeeding clip. Stacks of fan folded material within the scope of the invention can have any sheet in one clip joined to any sheet in a succeeding clip as long as dispensing of sheets from a preceding clip dispenses simultaneously at least one sheet of a succeeding clip so as to continue successive dispensing of the entire stack 10, as

desired. The sheets 22 in Figure 4 are also a plurality of individual sheets like those in Figure 3, although each sheet is not separately numbered as in Figure 3. The sheets 22 in Figure 3B are also a plurality of individual sheets like those in Figure 3. As seen in Figures 3A and 4A, a top view of a portion of the sheets in the clips shows the individual sheets of the clips can be separably joined together along weakened lines 24, such as lines of perforations 25, to ensure that the trailing sheet is in position for grasping by a user after the leading sheet is removed. Generally, the portion of the web of material between successive weakened lines defines each individual sheet. Folds 26, which are formed in the machine direction, generally define the width of the clip except for a situation like sheets 22a and the adjacent sheet in the full clip seen in Figure 3B. In use, the invention can be dispensed in the so-called pop-up format so that once the first sheet of the stack of fan folded sheets is dispensed through a dispenser orifice, each succeeding sheet will be at least partially pulled through the dispensing orifice before the leading sheet is fully separated from the succeeding sheet, as desired. That is, each sheet within the stack is separably joined to an adjacent sheet by either a weakened line relationship or an adhesive relationship, thus enabling, as desired, one-after-another dispensing for the entire stack once the initial sheet is dispensed. Alternatively, the invention could be used for so-called reach-in dispensing, and the user would have to actively assist in separating the lead sheet from the succeeding sheet each time dispensing is desired.

**Figures 5 and 5A** illustrate features for the slitter assembly 40, which can include pairs of shear slitters (i.e., one pair for each machine direction weakened line desired in the sheet of material), each pair including a perforated slitting blade 44 and a shear anvil 45. The basesheet material 31 can travel in the direction 41 through the slitter assembly. The perforated slitting blade seen in Figures 5 and 5A could be used in combination with the anvil roller 42 seen in Figure 1 (i.e., one blade 44 for each machine direction weakened line desired in the sheet of material, and this combination often referred to as crush or score slitting) to thereby form a weakened line (e.g., of perforations) in the web of material traveling between the slitting blades 44 and anvil roller 42. Alternatively, anvil 45 seen in Figures 5 and 5A could be positioned opposite perforated slitting blades like blade 44 to thereby form a weakened line (e.g., of perforations) in the web of material traveling between the perforated slitting blades 44 and paired anvils 45. The pairs of perforated slitting blades and anvils can be adjustable relative to one another to control perforation strength, as well as have a 0.0 to 0.5 degree or greater cant angle to improve cutting, if desired. The cant angle is defined as 43 in Figure 5A, which is the angle between the longitudinal axis 44b of the perforated slitting blade 44 and the longitudinal axis 45b of

anvil 45. Perforated slitting blade 44 could be formed by grinding notches into a sheer slitting blade or by notching a sheer slitting blade using an EDM (electric discharge machining) process, as well as by other techniques known to those of skill in the art for making a perforated slitting blade or structure. The perforated slitting blades and anvils  
5 can be made of hardened tool steel or similar materials. In addition to varying the overlap between the slitting blade and the anvil to control perforation strength, various configurations and dimensions can be used for the notches for the perforated slitting blades, such as a v-shaped notch measuring .040 inch wide and being .080 inch deep.

The perforated shear slitting blades could all be mounted on a common shaft (not  
10 shown) through a center hole 44a provided they do not have a cant angle, or some or all of them could be separately supported, each by means known to those of skill in the art. Similarly, the anvils could all be mounted on a common shaft (not shown) through a center hole 45a or some or all of them could be separately supported, each by means known to those of skill in the art. Figure 5A shows a portion of an anvil shaft 48 for shear  
15 slitting where there would not be the need for individual anvils 45, or how multiple anvils 45 could be mounted side by side along a common shaft. As such, an annular recess 49 would be needed opposite each perforated shear slitting blade. An example of an apparatus that could be readily employed to operate as the slitter assembly 40, in combination with the teachings herein and that of one of ordinary skill in the art, is  
20 disclosed in U.S. Pat. No. 4,570,518 of inventors Burmeister et al. of assignee Kimberly-Clark Corporation, and which is incorporated herein by reference. Other examples of slitter or cutter apparatus for use as the slitter or cutter assembly here are seen in U.S. Pat. Nos. 4,721,295 and 4,700,939 both of inventor Hathaway and of assignee Kimberly-Clark Corporation, and which are each incorporated herein by reference. Additionally or  
25 alternately, the slitter assembly could be like that sold by the Tidland Corporation of P.O. Box 1008, Camas, Washington, under the tradename Tidland™ Series C Class II Knifeholder, with slitter blades of Tidland™ part # 129839 crush cut (with notches ground in), 128401 shear cut (with notches ground in), and 133508 anvil slitter. It should be understood that other techniques and structures known to those of skill in the art for  
30 making a weakened line in a web of material could also be used to practice the invention, in combination with the teachings herein. The particular technique and structure used is not critical to the invention as long as the employed technique and structure can make the desired weakened line in the web of material as taught herein.

Referring to **Figures 2A and 6 to 6B**, inclusive, there are illustrated features of the  
35 arched roller assembly 50. The roller assembly 50 can be arching upward at an arc to form approximately equidistant lines from the rollers 57 to the nip rollers 76 at the bottom

of the fan folded sheet. For example, less arc is needed as the distance increases between the arched roller assembly and the nip rollers 76. Particularly, if the distance is sufficiently great, a conventional bowed roller assembly could be employed, and even little to no arc may be needed at sufficiently great distances. To achieve such arching as seen in the figures, a plurality of roller journal units 52 with each including a bearing unit 54, a journal shaft 56 and a roller 57, can be employed. The roller 57 fits over the unit 54 for rotation thereabout. Adjacent roller journal units 52 can be secured to one another using nuts and bolts to pass through tapped hole 53 and engage with threads 55 (Figure 6B), or by similar means for adjustably securing two such structures. The rollers can be made of stainless steel, Actel™ plastic or other similar/substitute materials, and the other components of the roller journal units can be made of conventional materials suitable for the circumstances.

**Figure 2A** in combination with **Figures 7 to 8A**, inclusive, illustrate features of the folding assembly 60, including folding boards 62. The folding board 62 of Figures 7 and 7A differs from that of Figures 8 and 8A by only the board's length, the number of mounting pins 64, and the relative location of the pin(s). Additional pins 64 could be used and the location can be varied depending on board length and the mounting mechanism available. The folding boards could be of varying lengths depending on folding and sheet material characteristics. For example, the boards could be a length equal to about  $\frac{1}{4}$  to  $\frac{1}{2}$  of the distance from the roller assembly 50 to the nip rollers 76. The folding boards like board 62 can be non-tapered along their length or tapered from one end to a second end, as seen in the drawings. If tapered, the boards 62 can be oriented in the folding assembly 60 so the taper points upwardly, i.e., the wider end of the board sits below the narrower end of the board. The folding boards 62 can be tilted by the mounting mechanism to achieve more or less taper of the front edge relative to the top end and the bottom end, for tapered or non-tapered boards 62. The folding boards can be made of stainless steel, Actel™ plastic or other similar/substitute materials which enable corrosion resistance and sanitary considerations to be met when making sheet products such as moistened baby wipes.

**Figures 2, 2A and 2B** illustrate a portion of an arched roller assembly and folding assembly for use with the present invention, similar to that seen in Figure 1. These figures show mounting bars 65a and 65b for mounting and positioning the folding boards as desired. Bars 66 can also be used to assist in aligning the fan folded material as it exits the folding board area and travels into the nip rollers 76. The number of boards 62 can be readily varied in order to achieve a desired folding pattern, as one of ordinary skill in the art would know to do in combination with the teachings herein, e.g., Figures 3, 3B,

3C and 4. Also, other folding techniques and structures could be employed to practice the invention, e.g., folding blades, folding pins or other techniques to mechanically push or guide the sheet into a desired folding pattern. In reference to Figure 2A for example, boards 62 can be adjustably secured to a conventional mounting mechanism similar to that seen here. As such, boards 62 mounted by bar 65a are positioned in the front of the material being fan folded (i.e., and such could be visible in a view like Figure 1) and boards 62 mounted by bar 65b are positioned in the back of the material being fan folded (i.e., and such could not be visible in a view like Figure 1). In this way the sheet of web material zigzags between the adjacent folding boards as it is folded from a flat sheet near the arched roller assembly 50 into a fan folded configuration beginning at the top of the folding boards nearest the roller assembly 50 down to the bottom of the folding board area and nearest the nip rollers 76.

As seen in Figure 2, and with reference to Figures 1 and 1A, the folding boards are spaced from each other a certain amount in both longitudinal and lateral directions. As the web being fan folded travels further down the folding boards and towards the nip rollers 76 the folding boards will be spaced closer together in both the longitudinal and lateral directions, and thereby the flat sheet material is fan folded into a ribbon-like structure including a plurality of fan folded sheets. The folding boards can be oriented in a fanned out configuration as seen in the Figures. Figure 2 shows a possible configuration for such boards. Theoretical fold lines extend parallel to each of the folding boards. Theoretical weakened lines extend parallel to every other folding board. Theoretical panels extend between each set of weakened lines. In practice, except for the center location, the actual weakened lines, panels and fold lines of the material being fan folded will often be askew relative to all of the respective theoretical locations discussed. Although the folding boards form the fold lines, the sheet of material will slide over the boards and gather towards the center of the sheet (i.e., the middle folding board seen in Figure 2) and the actual fold lines will often not be set until the material is past the folding board area and is ready to enter the nip rollers 76.

The ultimate orientation of all the folding boards as a group, as well as folding boards relative to one another, can depend on many factors. Such factors can include, without limitation, the characteristics of material being folded, the liquid add-on amount to the material, the strength of the weakened line between adjacent panels, operating speeds, necking of the material, desired folding pattern for the sheets, or distance between roller assembly 50 and the nip rollers 76. Adjusting these factors to enable a sheet of material to be fan folded in accordance with the invention can be done as would be known to one of ordinary skill in the art to do, in combination with the teachings herein.

For example, the tension of the sheet can be adjusted (e.g., a draw in the range of about 1% to about 10%, or about 3% to about 6% or about 4%) to enhance the folding process depending on one or more of the just-discussed factors. As another example and referring to Figure 1, to relieve CD tension on the sheet and/or assist it in passing through the folding assembly 60, the arched roller assembly 50 can be tilted backward to some degree (e.g., from about 1 degree to about 10 degrees or from about 3 degrees to about 7 degrees or about 5 degrees) from vertical seen at 58a to backward off vertical seen at 58b, and represented by angle 58. As yet another example, when employing such a tilted arched roller assembly, the folding boards can be spaced more towards the center of the web traveling through assembly 60 than would be suggested by theoretical fold lines. As still another example, the weakened lines, e.g., of perforations, can be positioned along the folding boards or theoretical fold lines or in between these. As yet another example, the sheet material could be any width to obtain a desired number of sheets in a clip. To obtain eight sheets as representatively seen in certain Figures, e.g., a sixty inch wide roll of basesheet material could be used and sheets measuring seven and one-half inches between perforated edge ends can be formed.

**Figures 9 and 10** schematically show representative steps for making a plurality of sheets 22 of the present invention for a wet or moistened product. Alternately, similar steps could be employed excluding any moistening step if a final dry product is desired, e.g., for tissues, toweling or other sheet-like products. Each of these steps can be specifically performed according to the teachings herein or as would be known to one skilled in the art, depending on particular circumstances, in combination with the teachings herein. These steps are described as follows, generally in the following order though not required. First steps 150 and 160 can be the same, namely, providing a basesheet for forming into a plurality of sheets. After step 150 is step 151 of converting the basesheet into one or more sheets separably joined together by a weakened line. This usually includes forming several panels from a larger basesheet of material. After the forming of individual panels, converting also includes fan folding the sheets such as to form a ribbon of fan folded sheets. Next, adhesive can be applied to the top fan folded sheet in step 152. Then the elongated fan folded sheets, or ribbon, are cut into clips, in step 153. Next, a second clip is placed on top of the first sheet of the below clip of sheets and joined to the first sheet with adhesive applied thereto, in step 154. As used herein "applying" means any way to get adhesive onto the two sheets that are adhesively joined together, which can include without limitation, spraying, rolling, squirting, drooling, painting, coating and/or printing. This also includes getting the adhesive onto the two sheets in any order (as between the two sheets being joined by adhesive) or



simultaneously. Next, the stack of sheets is ready for the final steps of 155/156 or 157/158, which include packaging and moistening, in either order as shown. The sheets are now ready for consumption by a user.

**Figure 10** shows an alternate set of steps for making sheets of the invention. The principal difference is that here, the basesheet is moistened in step 162 in advance of applying adhesive in step 164. Although converting in step 161 is shown to precede moistening step 162, steps 161 and 162 can be reversed and they can occur near simultaneously, all dependent upon how many sub-steps are employed in the converting step 161. Such sub-steps are known to those of skill in the art and are often driven by economics or equipment to obtain a desired fold for the plurality of sheets. Otherwise, steps 163 to 166 are analogous to above described steps 153, 152, 154 and 155/158 respectively. To the degree not specifically discussed, the various features set forth herein or illustrated in the drawings can be made with structures and by techniques known to those of ordinary skill in the art.

**Figure 18** representatively shows an alternate apparatus and process for forming a stack of fan folded material in accordance with the present invention. Boxes 410a, 410b to 410n will be referred to in relation to **Figure 18** as the ribbon forming stations 410a, 410b, etc. to 410n. Each ribbon forming station schematically depicts the equipment and process discussed previously in relation to **Figures 1 to 10**, inclusive, in so far as that process begins with the roll 30 of basesheet material 31 and continues to the nip rollers 76. The ribbon forming station forms a ribbon, such as each ribbon 411a from 410a, 411b from 410b, 411(n-1) from 410(n-1) (not shown), to 411n from 410n, where n could be as many ribbon forming stations as desired. Based on the previous discussion, each ribbon comprises a plurality of fan folded panels made from the basesheet material. At least two ribbons, and up to n desired ribbons, can be separably joined to each adjacent ribbon to form a ribbon stack 408. The size of the ribbon stack is determined by the number of individual sheets 22 (**Figures 3 to 3C**, inclusive) desired in the formed stack 10 of fan folded material, where each sheet from the top most sheet in the stack to the bottom most sheet in the stack is separably joined to its respective adjacent sheet in the stack.

More particularly, the process for forming a stack of fan folded material as representatively depicted in **Figure 18** can include the following steps, advantageously in this order though such order may not be required. First, via each ribbon station (see **Figure 1** and supporting figures and description previously), an elongate web of material 31 is provided; the elongate web of material 31 is weakened along a plurality of lines 25 to form a plurality of panels 28 joined to adjacent panels 28 along the plurality of lines 25; and, the plurality of panels 28 are folded together to form a first ribbon 411a of panels.

Ribbon 411a is assisted by pull roller 82 and is carried by support belt 412. Belt 412 operates with support rollers 414. A sufficient amount of adhesive 417 can be applied by adhesive nozzle 416 to a top portion of the first ribbon, e.g., a portion of the top sheet. A succeeding ribbon 411b of panels can be formed by ribbon forming station 410b from a second elongate web of material. Ribbon 411b then is assisted by a second pull roller 82 and is joined to the first ribbon 411a by separably joining (e.g., with adhesive 417) the top portion of the first ribbon 411a to a bottom portion of the succeeding ribbon 411b (e.g., a portion of the bottom sheet of ribbon 411b) to form a ribbon stack 408.

From there, a next ribbon, similar to ribbons 411a and 411b, can be formed and separably joined to ribbon 411b, and so on until ribbon 411(n-1). Ribbon 411(n-1) is formed similar to the previous ribbons and is separably joined to the preceding ribbon, except, rather than being adhesively joined, ribbon 411(n-1) can be interfolded with the preceding ribbon, e.g., where the bottom sheet of ribbon 411(n-1) is interfolded with the top sheet of the preceding ribbon. Interfolding is represented schematically by box 418, and such can be accomplished with conventional equipment and techniques, e.g., that known as a machine called NEPTUNE™ that produces interfolded ribbons that are interfolded together (using one of a variety of fold types) sold by The Paper Converting Machine Company of 2300 S. Ashland Ave., Green Bay, Wisconsin 54307 ("PCMCP"). The NEPTUNE™ machine could be modified, in combination with the teachings herein, to obtain the desired interfolded ribbon(s). Alternatively, a set of horizontal plates could be used to tuck the top sheet of the lower ribbon over the bottom sheet of the upper adjacent ribbon. This configuration of plates may have to be custom designed based on the material to be folded, the width of the stack, and the amount of overlap desired, but one of ordinary skill in the art would be able to readily design an operable plate configuration. Next, ribbon 411n, similar to the preceding ribbons, can be formed and separably joined (e.g., by adhesive or interfolding or other means for separably joining, although one is not specifically shown in the figure) to ribbon 411(n-1) to form a larger ribbon stack 408a. It should also be understood that each time one ribbon is separably joined to an adjacent ribbon this can be accomplished by the same technique (e.g., only adhesive, only interfolding, etc.) or any combination of separably joining means, as such means are provided in the definition of separably joining first discussed above.

The fully formed ribbon stack can then pass between a nip roller 422 (which could be a roller only or a belt type nip mechanism) and belt 412 as it progresses into a ribbon saw 420 zone. The ribbon saw 420 moves up and down to cut the ribbon stack at a desired interval and, e.g., in the cross machine direction, to thereby form a stack 10 of fan folded material comprising n ribbons that have each been separably joined together. For

example, the ribbon saw 420 could be any conventional log saw such as part of the NEPTUNE™ or MERMAID™ converting machines sold by PCMC. Alternatively, a variety of other conventional log saw machines could be used such as those sold by PCMC or others. Stack 10 then moves along toward packaging equipment on a packaging belt 426 which operates with package belt support rollers 424. At this point, the process is now similar to what happens to stacks 10 discussed in relation to Figures 1-10, inclusive, after the stacks 10 are formed from stacked clips 20. A plurality of stacks of fan folded material similar to stack 10 (Figure 18) can be continuously formed from the ribbon stack as the ribbon stack is formed and advances and the saw 420 moves up and down to cut the ribbon stack at desired intervals. The stacks 10 in Figure 18 can be made dry or wet, similar to those in Figure 1.

Referring generally to the figures now, the plurality of sheets 22, such as a stack 10 of sheets, can include any suitable number of individual sheets depending upon the desired packaging and end use. For example, the stack 10 can be configured to include at least about 5 wet wipes and desirably from about 16 to about 320 individual sheets, and more desirably from about 32 to about 160 sheets. The size and shape of the stack of sheets 22 is dependent upon the size and shape of the package/dispenser and vice versa. For example, the length of an assembled stack of wet wipes sheets can be about 190mm, with a height of about 90mm and a width of about 100mm.

Each sheet is generally rectangular in shape and defines a pair of opposite side edges and a pair of opposite end edges which can be referred to as a leading end edge and a trailing end edge. Each sheet defines an unfolded width and an unfolded length. The sheets can have any suitable unfolded width and length. For example, sheets of wet wipes can have an unfolded length of from about 2.0 to about 80.0 centimeters or from about 10.0 to about 26.0 centimeters and an unfolded width of from about 2.0 to about 80.0 centimeters or from about 10.0 to about 45.0 centimeters.

Materials suitable for the sheets of the present invention are well known to those skilled in the art. The sheets can be made from any material suitable for use as a wipe, including meltblown, coform, airlaid, bonded-carded web materials, spunlace, hydroentangled materials, high wet-strength tissue and the like and can comprise synthetic or natural fibers or combinations thereof. For wet wipes, they can have a dry basis weight of from about 25 to about 120 grams per square meter or from about 40 to about 90 grams per square meter.

In a particular aspect, sheets of wet wipes of the present invention can comprise a coform basesheet of polymeric microfibers and cellulosic fibers having a basis weight of from about 60 to about 100 grams per square meter or about 80-85 grams per square

meter. Such coform basesheets can be manufactured generally as described in U.S. Patent No. 4,100,324 to Anderson et al. which issued July 11, 1978, and which is herein incorporated by reference. More particularly, such coform basesheets can be manufactured as are described as part of recently filed U.S. Patent Application Serial No. 09/751329, filed on December 29, 2000 entitled, "Composite Material With Cloth-like Feel" of inventors Scott R. Lange et al., and which is incorporated herein by reference.

Typically, such coform basesheets comprise a gas-formed matrix of thermoplastic polymeric meltblown microfibers, such as, for example, polypropylene microfibers, and cellulosic fibers, such as, for example, wood pulp fibers. The relative percentages of the polymeric microfibers and cellulosic fibers in the coform basesheet can vary over a wide range depending on the desired characteristics of the wet wipes. For example, the coform basesheet can comprise from about 20 to about 100 weight percent, from about 20 to about 60 weight percent, or from about 30 to about 40 weight percent of polymeric microfibers based on the dry weight of the coform basesheet being used to provide the wet wipes. An example of such a coform basesheet for use in the present invention is found in the baby wipes product presently sold by Kimberly-Clark Corporation and known as HUGGIES® Natural Care.

In another aspect of the invention, wipes 22 can contain a liquid which can be any solution which can be absorbed into the wipes, thus making them "wet wipes." The wipes can be moistened at any time before the wipes are actually used by the consumer. They can be moistened some time during the manufacturing process before or contemporaneous with the plurality of wipes being sealed in a dispenser or other packaging for next use by a product user. The liquid contained within the wet wipes can include any suitable components which provide the desired wiping properties. For example, the components can include water, emollients, surfactants, preservatives, chelating agents, pH buffers, fragrances or combinations thereof. The liquid can also contain lotions, ointments and/or medicaments. An example of such a liquid for use in the present invention is found in the baby wipes product presently sold by Kimberly-Clark Corporation and known as HUGGIES® Natural Care.

The amount of liquid or solution contained within each wet wipe can vary depending upon the type of material being used to provide the wet wipe, the type of liquid being used, the type of container being used to store the stack of wet wipes, and the desired end use of the wet wipe. Generally, each wet wipe can contain from about 25 to about 600 weight percent or from about 200 to about 400 weight percent liquid based on the dry weight of the wipe, for improved wiping in certain situations. To determine the liquid add-on, first the weight of a just-manufactured dry wipe is determined. Then, the

amount of liquid by weight equal to the weight of the just-manufactured dry wipe, or an increased amount of liquid measured as a percent add-on based on the weight of the just-manufactured dry wipe, is added to the wipe to make it moistened, and then known as a "wet wipe" or "wet wipes". In a particular aspect wherein the wet wipe is made from a

5 coform material comprising from about 30 to about 40 weight percent polymeric microfibers based on the dry weight of the wipe, the amount of liquid contained within the wet wipe can be from about 250 to about 350 weight percent or about 330 weight percent based on the dry weight of the wet wipe. If the amount of liquid is less than the above-identified range, the wet wipes can be too dry and may not adequately perform depending

10 on the intended use. If the amount of liquid is greater than the above-identified range, the wet wipes can be over saturated and soggy and the liquid can pool in the bottom of the container, as well as contribute to problems with the adhesive 92 sticking to the surface of wet wipe sheets 22.

The plurality of sheets 22 of the present invention, e.g., wet wipes, can be

15 arranged in a package or dispenser in any manner which provides convenient and reliable one at a time dispensing, and for wet wipes which assists the wet wipes in not becoming overly dry. An example of non-rigid containers for use with the present invention are disclosed in U.S. Serial No. 09/813,536, filed March 21, 2001 and entitled "STORAGE AND DISPENSING PACKAGE FOR WIPES" and assigned to the assignee of the present

20 application, which prior application is incorporated fully herein by reference. **Figures 11 and 12** show one such storing and dispensing package 240 for wipes or sheets 22. The package 240 includes a non-rigid container 242 having sides 250 with a top end portion 252 and a bottom end portion 254, where the sides and top and bottom end portions define a cavity 256 within the container 242.

25 The cavity 256 includes a storage portion 258 for wipes 22. The top end portion 252 can include a resealable mechanism 200. A non-rigid baffle structure 210 has a width and is located in between the resealable mechanism 200 and the storage portion 258 with the baffle structure 210 positioned between opposing sides 250 of the container spaced apart from each other. The baffle structure thereby defines a dispensing portion

30 260 of the cavity 256 overlying the storage portion 258 of the cavity. As seen in Figure 11, the resealable mechanism 200 is in a sealed closed position 202, whereas in Figure 12 it is in an open position with a wipe 22 inside the container ready for pop-up dispensing. The mechanism 200 can be any type of mechanism that allows the package 240 to be opened, closed and reopened multiple times during the life of the package, e.g.,

35 a zipper with or without a stopper, resealable adhesive, a clip or other structure that achieves the result desired here.

In use, the resealable mechanism 200 is opened and then access to the dispensing portion 260 is gained. The user then passes his or her hand, etc., through the orifice 280 to grab the first wipe in the stack of wipes. If the orifice is a frangible seal, this must be broken before the user can pass his or her hand through the orifice. Once the user grabs the wipe, it can then pass through the orifice and enter the dispensing portion 260 as the user pulls it up. If the user does not immediately need the wipe, it can be left in the orifice partially dispensed where it can be maintained in place by the baffle structure 210 until desired later. The partially dispensed wipe will just rest in place in the orifice, part in the dispensing portion and part in the storage portion, conveniently ready for later dispensing in the pop-up format. If the user does immediately desire to use the wipe, it can pass the complete wipe through the dispensing portion and out of the package. For pop-up dispensing, the wipe will become separated or disjointed from the subsequent adjacent second wipe at a separably joined interface (e.g., weakened line, adhesive joint, or other mechanism) after fully dispensing the first wipe and while a portion of the second wipe remains in the opening or orifice 280. The next wipe for dispensing may be automatically maintained in the orifice partially dispensed for later use (i.e., in a pop-up dispensing format). Alternatively, the following wipe may need to be fetched out of the storage portion similar to the first wipe at a later time when it is desired, commonly called reach-in dispensing, if the user pushed the following wipe back into the storage portion after pop-up dispensing of the leading wipe. In either case, after the desired number of wipes are taken, the resealable mechanism can be sealed closed, with or without a wipe partially dispensed in the dispensing portion, as discussed previously. At a later time when another wipe(s) is desired, the preceding steps can generally be followed again. In this regard, the user can pull a subsequent third wipe through the dispenser opening and then separating the third wipe from a subsequent adjacent fourth wipe at a separably joined interface between the third and fourth wipes. Depending on the number of sheets in a clip and where in the stack dispensing is occurring, the separably joined interface can be a different type of separably joined interface than that of the previously separated first and second wipes. It should be understood that reference here to first, second, third and fourth wipes or sheets does not mean only sequential sheets one, two, three, and four (i.e., though it can refer to these also), but rather, such is used for reference purposes to refer to different sheets within a clip or stack of sheets and in relation to when in time such sheets are dispensed relative to one another.

An example of rigid containers suitable for use with the present invention are disclosed in U.S. Serial No. 09/538,711 filed March 30, 2000 entitled "WET WIPE CONTAINER WITH FLEXIBLE ORIFICE" and assigned to the assignee of the present

application, which prior application is incorporated fully herein by reference. **Figure 13** shows such a rigid plastic wet wipe dispenser 300. Dispenser 300 includes a top 301 hingedly attached to a base 302 and a removable inner cover 303. The removable inner cover contains a pop-up style wipe dispenser including a rigid port 305 which surrounds a flexible, rubber-like material or sheet 306 having a dispensing opening 307. The dispensing opening 307 is illustrated as several slits through which individual wet wipes are removed from the container. The cover is removably secured to the sidewalls of the base by a small lip around the periphery of the inner cover that engages notches with several protruding ribs on the inner surface of the sidewalls (not shown). It also rests on a small support surface in each of the four corners of the base, which is outwardly visible by discontinuities 308 in the rounded corners of the base. The top is secured in a closed position by a suitable latching mechanism, in which a protrusion 309 in the front lip of the base is engaged by an opening 311 in the front lip of the top. The shape of the rigid port in the embodiment shown in Figure 13 is oval, but can be any shape and size large enough to enable the user to reach into the container with their fingers to grasp the next available wet wipe in the event of a dispensing failure, or if reach-in dispensing is preferred to further aid in moisture retention of the wipes. Generally, use of dispenser 300 for dispensing wipes 22 is similar to that for package 240, except when due to obvious structural differences.

Table

Separably Joined Inter-face	Width of Sheet (cm)	Dispens- ing Force (g/sheet)  <u>Type 1 Dispenser</u>	Dispens- ing Force per unit Width (g/cm) <u>Type 1 Dispenser</u>	Dispens- ing Force (g/sheet)  <u>Type 2 Dispenser</u>	Dispens- ing Force per unit Width (g/cm) <u>Type 2 Dispenser</u>	Dispens- ing Force (g/sheet)  <u>Type 3 Dispenser</u>	Dispens- ing Force per unit Width (g/cm) <u>Type 3 Dispenser</u>
Adhesive	18.75	555.5	29.6	474.7	25.3	437.1	23.3
Perfor- ations	18.75	368.2	19.6	371.2	19.8	337.0	20.1

The Table sets out data obtained from samples made in accordance with the teachings of the invention. Samples were made from a basesheet of coform comprising the same material known as the baby wipes product currently available from Kimberly-Clark Corporation of Neenah, Wisconsin under the tradename HUGGIES® Natural Care and moistened with 330% add-on of that solution set forth in pending U.S. Patent Application Serial No. 09/464418, filed on December 16, 1999 entitled, "Wet Wipes Containing A Monoalkyl Phosphate" of inventors Cole et al., and which is incorporated herein by reference. The samples labeled as "Adhesive" were two adjacent sheets, e.g.,

22a and 22b, from two clips of sheets separably joined together by adhesive, whereas the samples labeled as "Perforations" were two adjacent sheets within a clip of sheets separably joined to each other by a line of perforations. The Adhesive samples used the same hot melt adhesive, commonly known as RT 2730 APAO sold by Huntsman  
5 Polymers Corporation of 2502 South Grandview, Odessa, Texas 79766. The adhesive was applied to the moistened coform with a one port spray head part # 103968 and MR1300 transfer block manufactured by ITW Dynatec (see below). The spray head was fitted with a swirl nozzle, part # 057B1922 with a 0.020 inch orifice, spraying a continuous pattern approximately 18 mm away from the moistened basesheet. The adhesive was  
10 provided from a Dynamelt™ melt tank and pump system, model #084E428, manufactured by ITW Dynatec of 31 Volunteer Drive, Hendersonville, Tennessee. An ITW Dynatec 16-foot long transport hose, part # 101088D, fit to the spray head and supplied the melted adhesive from the melt bank to the spray head. The adhesive was applied in a substantially uniform swirl pattern about 1.25 cm wide along a leading edge (i.e., the  
15 width) of the top wipe in the clip, similar to that seen in Figure 1.

Alternatively, and using the same type of adhesive, the adhesive could be applied to the moistened coform with a Slice applicator, part number 1021281, manufactured by Nordson Corp. of 2905 Pacific Drive, Norcross, Georgia. The gear pump within the slice  
20 applicator could be driven by a servo motor to ensure the adhesive gets applied to the coform at a rate in direct proportion to the web speed. As such, the applicator could be fitted with a Summit nozzle, part number 1020687, 1/2 inches wide with 1 psi air pressure (also from Nordson Corp.) and located 20-25mm above the wet coform.

To prepare the samples, the basesheet material was formed into fan folded clips of eight sheets, similar to than in Figure 3C, each sheet in the clip separably joined to an  
25 adjacent sheet(s) by perforations. Perforation refers to the amount of cutting and the distance between the cuts in the perforation that separates the sheets in a clip. There are three parameters to this measurement: cut length, bond length and bond spacing. The bond spacing is equal to the sum of the cut length plus the bond length. By way of example, perforations that are useful with sheets, e.g., wet wipes of the invention, are  
30 ones that have a bond length in the range of 0.070 inch (1.75 mm) to 0.020 inch (.5 mm), a cut length in the range of 0.055 inch (1.375 mm) to 0.73 inch (18.25 mm), and a bond spacing in the range of 0.125 inch (3.125 mm) to 0.75 inch (18.75 mm). Ultimately, however, desired perforation configurations are dependent upon many factors including basesheet characteristics (e.g., fiber composition, formation process, bulk, density,  
35 thickness, weight, CD tensile, MD tensile), desired dispensing characteristics (e.g., type of dispensing, type of dispenser, wet or dry dispensing) and others that can affect how one



sheet separates from another sheet and/or dispenses from a dispenser. The sheets seen as the samples labeled "Perforations" in the Table had a detach force as determined herein of about 453 grams per sheet. Ten clips were adhesively joined together to form a stack of wet wipes sheets.

5           The adhesive was applied to the top surface of the first wet wipe of a clip moving at a speed of about 320 ft/minute. The adhesive was maintained at about 375 degrees Fahrenheit and system pressures were adjusted to obtain the desired add-on through the nozzle of about 0.00060 grams/wipe. Then, the second wipe was laid on top of the first wipe with adhesive thereon within about 3-4 seconds. About 2 seconds later, a pressure  
10       about 1/3 psi was uniformly applied on top of the second wipe for fractions of a second to a few seconds. This pressure could vary from 0 (i.e., the weight of the clip of wipes itself) to 2 psi (i.e., by the use of an additional force), as well as possible other pressures. The stack of wipes with adhesive applied thereon were placed in a sealed container, such as a plastic bag and allowed to rest for 2 to 6 days. The sealed container of wipes was then  
15       placed in a test lab and allowed to equilibrate to room temperature of about 20 degrees Celsius for 24 hours, remaining sealed in the container until testing. The samples were then measured for the force needed to separate or detach two separably joined wipes, in the manner explained below in reference to Figures 16 and 17.

          The test for measuring the dispensing force for wipes uses a SINTECH™ Model #  
20       M4001 with a MTS 25 pound (11.4 Kg) load cell conventional test machine equipped with TestWorks™ 3.10 software for Windows, or comparable equipment, is used. Both the Sintech™ test machine and TestWorks™ software are available from MTS Corporation located at 1400 Technology Drive, Eden Prairie, Minnesota, USA. The testing is done, generally, under TAPPI standard procedures and conditions which would be applicable  
25       except as otherwise noted. The measurement procedure begins by providing a dispenser with separably joined wipes therein for dispensing. The dispenser is secured to a fixed portion of the test machine (e.g., by hand or otherwise) with the dispensing orifice centered below an upper movable test machine jaws. The wipe to be tested is carefully threaded through the dispenser orifice so that about 1 inch (2.5 cm) of the leading edge of  
30       the wipe protrudes through the orifice for securing to the upper movable jaws. The upper jaws are positioned so that the grip area (which is about 4.5 inches by .5 inches (11.25 cm by 1.25 cm)) is clamped to the center end portion (about 4 inches by 1 inch (10 cm by 2.5 cm)) of the wipe waiting to be dispensed. The test machine is then activated to move the upper jaws away from the dispenser (e.g., the upper jaws and/or the dispenser could  
35       move relative to the machine) at a speed of about one hundred (100) cm/min until the wipe is completely passed through the dispenser orifice and completely disjointed from

the following separably joined wipe. The disjointing of the two wipes may occur from the outside edges in, but could also occur from the inside out, from one side to the other or at one or more points between the sides. The actual tear propagation pattern is not critical, but rather, determining the peak load during test dispensing is the goal. The force in grams (g) as a function of the distance of the jaws movement relative to the machine is recorded using the TestWorks™ 3.10 software. The peak load exhibited during the test is designated as the dispensing force, in grams of force (g), for the wipe. The peak load data for the perforation joint was obtained by measuring the peak load for seven perforation joined sheets in a clip of eight sheets and taking the average of the seven measurements. The peak load data for the adhesive joint was obtained by measuring the peak load for three or four adhesively joined sheets between five clips of eight sheets and taking the average of the four measurements. The dispensing force per unit width or "normalized dispensing force" as used herein, is the dispensing force divided by the width of one sheet along the separably joined edge adjacent the second sheet.

To obtain the dispensing force data for the table, the identified samples were dispensed from three different dispensers, following the above test procedure. Type 1 was that known as currently available PAMPERS® One-Ups!™ of the Procter & Gamble Company of Cincinnati, Ohio 45202, USA. Type 2 was that seen in Figure 1 (i.e., the shown flexible orifice but with the container like that seen in Figure 2) of a U.S. Patent application filed separately but concurrently herewith entitled, "FLEXIBLE ORIFICE FOR WET WIPES DISPENSER" of inventors Yung H. Huang et al., U.S. Serial No. 09/870814, assigned to the same assignee of this application and known by attorney docket number 16981A, which application is incorporated fully herein by reference. Type 3 was that seen in Figure 2 of the just cited U.S. Patent application filed separately but concurrently herewith entitled, "FLEXIBLE ORIFICE FOR WET WIPES DISPENSER" of inventors Yung H. Huang et al.

**Figures 16 and 17** (with reference to Figures 3A and 4A for weakened line joint 94 and to Figures 14A to 15B inclusive which specifically show two possible adhesively joined configurations), illustrate the test for measuring the detach for two separably joined wipes. Figures 16 and 17 specifically show two adhesively joined sheets being separated, and though not shown two perforation joined sheets would be similar except as noted below. The testing is done, generally, under TAPPI standard procedures and conditions which would be applicable except as otherwise noted. A SINTECH™ Model # M4001 with a MTS 25 pound (11.4 Kg) load cell conventional test machine 170 equipped with TestWorks™ 3.10 software for Windows, or comparable equipment, is used. Both the

Sintech™ test machine 170 and TestWorks™ software are available from MTS Corporation located at 1400 Technology Drive, Eden Prairie, Minnesota, USA. The measurement procedure begins by providing two separably joined wipes, e.g., carefully removing two adhesively joined wipes or two perforation joined wipes from a stack of  
5 wipes without materially disrupting the joint between the two wipes. Next, the distance between two jaws 172, 174 of machine 170 are set about two inches (5 cm) shorter than the end to end distance (perpendicular to the joint 94) of the wipes 22. For two adhesively joined wipes as in Figures 14A and 15A, the joint is seen as 94. For two perforation joined wipes as seen in Figures 3A and 4A, the joint is seen as line 24. Grip area 176 of  
10 each jaw is about 4.5 inches by .5 inches (11.25 cm by 1.25 cm). For two adhesively joined sheets, the non-joint center end portion (about 4 inches by 1 inch (10 cm by 2.5 cm)) of one wipe is clamped to upper jaw 172 while the non-joint center end portion (about 4 inches by 1 inch (10 cm by 2.5 cm)) of the adjoining wipe is clamped to lower jaw 174. For two perforation joined sheets, they are first folded in half along the axis  
15 perpendicular to the perforation joint, and then they are placed in jaws 172 and 174 similar to that for adhesively joined sheets. The initial distance between jaws is about 6 inches (15 cm), but this can vary depending on sheet size. The perforation line is about centered between the upper and lower jaws. Machine 170 is then activated to move the jaws away from each other, e.g., one or both jaws moving relative to the machine, at a  
20 speed of about one-hundred (100) cm/min until the joint between the two wipes completely breaks and the two once separably joined wipes are completely disjointed from each other. The disjointing of the two wipes may occur as seen in Figure 17, e.g., from the outside edges in, but could also occur from the inside out, from one side to the other or at one or more points between the sides. The actual tear propagation pattern is not  
25 critical, but rather, determining the peak load during testing is the goal. The force in grams (g) as a function of the distance of the jaws movement relative to the machine is recorded using the TestWorks™ 3.10 software. The peak load exhibited during the test is designated as the detach force, in grams of force (g), between two separably joined wipes. The detach force per unit width or "normalized detach force" as used herein, is the  
30 detach force divided by the width of one sheet along the separably joined edge adjacent the second sheet.

As a result of their work, and samples representatively seen in the Table, the inventors have determined that particular force relationships between the plurality of sheets 22, as well as between clips 20, are better than others for overcoming some  
35 challenges to successively dispensing wipes one at a time more successfully. Such can be beneficial to, e.g., easier wipe retrieval, reducing the likelihood of wipe fallback into the

container and/or reducing the likelihood of multiple wipes dispensing when only a single wipe is desired, and the balancing/interaction of these features. For example, the inventors have discovered that the separably joined relationship between adjacent weakened line joined sheets can use a normalized detach force in the range of, and in order of increasing advantage: about 5.3 g/cm to about 42.7 g/cm, about 8 g/cm to about 32 g/cm, about 10.7 g/cm to about 24 g/cm, or about 16 g/cm to about 21.3 g/cm. For similar reasons, the inventors have discovered that the separably joined relationship between adjacent sheets that are adhesively joined can use a normalized detach force for the adhesively joined sheets that is in the range of, and in order of increasing advantage: equal to or less than the normalized detach force for weakened line joined sheets, 30% to 90% of the normalized detach force for weakened line joined sheets, or 40% to 70% of the normalized detach force for weakened line joined sheets. The actual desired normalized detach force for adhesively joined sheets is dependent upon the weakened line characteristics (e.g., detach force) and dispenser and/or dispensing characteristics. For still similar reasons, the inventors have discovered that while the detach force for different types of separably joined relationships can vary, and may advantageously vary depending on various factors above, for dispensing of sheets with such relationships the two different separably joined relationships will advantageously be dispensed using dispensing forces which vary by no more than, in reference to the larger force, and in order of increasing advantage: about 35 %, about 20%, about 10%, or about 0%. Still further, the inventors have discovered that the dispensing force employed to dispense a wipe from a stack of wipes including at least two separably joined sheets having different separably joined relationships, will be in the range of, and in order of increasing advantage: about 3.2 g/cm to about 37.3 g/cm, about 5.3 g/cm to about 32 g/cm, about 8 g/cm to about 26.7 g/cm, or about 10.7 g/cm to about 21.3 g/cm, all for a normalized dispensing force between the separably joined wipes. As concerns the relationship of the dispensing force to the detach force for the perforation joined sheets, one can employ a dispensing force that is less than or equal to the detach force necessary to break the perforations. As concerns the relationship of the dispensing force to the detach force for the adhesively joined sheets, one can employ a dispensing force that can be equal to, less than or greater than the detach force necessary to break the perforations, all dependent upon basesheet characteristics and the type of separably joined relationship between adjacent sheets.

When comparing the dispensing force to the detach force, one needs to understand that the detach force is not dependent upon dispensing characteristics. That is, the detach force is dependent merely upon basesheet characteristics (e.g., fiber composition,

formation process, bulk, density, thickness, weight, CD tensile, MD tensile) and the perforation configuration. Differently, the dispensing force is dependent upon not only basesheet characteristics (e.g., fiber composition, formation process, bulk, density, thickness, weight, CD tensile, MD tensile) and the perforation configuration, but also  
5 dispensing characteristics (e.g., type of dispensing, type of dispenser, wet or dry dispensing).

Without being limited to a theory of operation, the inventors believe they may understand why perforation joined sheets and adhesively joined sheets can have different detach forces and yet can advantageously have similar dispensing forces. For example,  
10 as a wipe passes through the dispenser orifice, if it is a weakened line separably joined wipe (e.g., by perforations) it begins to become disjointed from the following wipe discontinuously, i.e., a few perforations at a time until eventually all of the perforations are broken and the first wipe is completely disjointed from the second wipe and fully dispensed from the dispenser. Differently, if the wipe is separably joined to a following  
15 wipe by an adhesive joint, it tends to become disjointed from the following wipe continuously, i.e., the entire adhesive joint becomes completely disjointed from the second wipe at about the same time, and it is then fully dispensed from the dispenser. Thus, considering a graphical representation of force as a measure of time, the force curve for the perforation relationship will not experience as great a peak force during dispensing  
20 and instead it will be a more smoothed out curve distributing the force over a greater time period. Oppositely, the force curve for the adhesive relationship will experience a greater peak force during dispensing and it will be a shorter curve concentrating more force over a shorter time period. In summary, the inventors have determined that, in one aspect of the invention, providing wipes which enable a more uniform dispensing force to be used  
25 regardless of the separably joined relationship between multiple wipes in a clip or stack of wipes is desirable for improved pop-up dispensing.

All publications, patents, and patent documents cited in the specification are incorporated by reference herein, as though individually incorporated by reference. In the case of any inconsistencies, the present disclosure, including any definitions herein, will  
30 prevail. While the invention has been described in detail with respect to the specific aspects thereof, it will be appreciated that those skilled in the art, upon attaining an understanding of the foregoing, may readily conceive of alterations to, variations of, and equivalents to these aspects which fall within the spirit and scope of the present invention, which should be assessed accordingly to that of the appended claims.

We Claim:

1. A stack of fan folded material comprising:  
at least two clips of fan folded material;  
5 each clip comprising a plurality of fan folded sheets, each sheet joined to at least one adjacent sheet by a weakened line; and  
each clip joined to an adjacent clip by a sheet of one clip being separably joined to a sheet of a succeeding clip.
- 10 2. The stack of claim 1 wherein the weakened line comprises perforations.
3. The stack of claim 1 wherein the weakened line is formed in a machine direction of the sheets.
- 15 4. The stack of claim 1 wherein the plurality of fan folded sheets comprise fold lines formed in a machine direction of the sheets.
5. The stack of claim 1 wherein separably joined comprises adhesively joined or interfolded.
- 20 6. The stack of claim 1 further comprising a liquid in combination with the stack of fan folded material, the liquid at an add-on rate of about 25 to about 600 weight percent based on a dry weight of the stack of fan folded material.
- 25 7. A stack of fan folded material comprising:  
at least two clips of fan folded material;  
each clip comprising a plurality of fan folded sheets folded along a machine  
direction of the sheets, each sheet joined to at least one adjacent sheet by a weakened  
line formed in the machine direction of the sheets; and  
30 each clip joined to an adjacent clip by a last sheet of one clip being adhesively  
joined to or interfolded with a first sheet of a succeeding clip.
8. The stack of claim 7 wherein the weakened line comprises perforations.

9. The stack of claim 7 further comprising a liquid in combination with the stack of fan folded material, the liquid at an add-on rate of about 25 to about 600 weight percent based on a dry weight of the stack of fan folded material.
- 5 10. A process for forming a stack of fan folded material comprising:  
providing an elongate web of material;  
weakening the elongate web of material along a plurality of lines to form a plurality  
of panels joined to adjacent panels along the plurality of lines;  
folding the plurality of panels together;  
10 cutting the plurality of panels to form a plurality of clips; and  
joining each clip to an adjacent clip by separably joining a bottom portion of one clip  
to a top portion of a succeeding clip.
11. The process of claim 10 wherein weakening comprises perforating along the  
15 plurality of lines.
12. The process of claim 10 wherein weakening comprises weakening along the  
machine direction of the panels.
- 20 13. The process of claim 10 wherein folding comprises folding the plurality of panels  
along the machine direction of the panels.
14. The process of claim 10 wherein separably joining comprises adhesively joining.
- 25 15. The process of claim 10 further comprising adding a liquid at an add-on rate of  
about 25 to about 600 weight percent based on a dry weight of the elongate web of  
material.
16. The process of claim 10 further comprising folding each sheet upon itself at least  
30 once.
17. The process of claim 10 wherein cutting the plurality of panels occurs in the cross  
machine direction.
- 35 18. A process for forming a stack of fan folded material comprising:  
(a) providing an elongate web of material;

(b) weakening the elongate web of material along a plurality of lines to form a plurality of panels joined to adjacent panels along the plurality of lines;

(c) folding the plurality of panels together to form a first ribbon of panels;

(d) repeating steps (a) to (c) for at least a second elongate web of material and thereby forming at least one succeeding ribbon of panels; and

(e) joining the first ribbon to the succeeding ribbon by separably joining a top portion of the first ribbon to a bottom portion of the succeeding ribbon to form a ribbon stack.

10 19. The process of claim 18 wherein weakening comprises perforating along the plurality of lines.

20. The process of claim 18 wherein weakening comprises weakening along the machine direction of the panels.

15

21. The process of claim 18 wherein folding comprises folding the plurality of panels along the machine direction of the panels.

20 22. The process of claim 18 wherein separably joining comprises adhesively joining or interfolding.

23. The process of claim 18 further comprising adding a liquid at an add-on rate of about 25 to about 600 weight percent based on a dry weight of the elongate web of material.

25

24. The process of claim 18 further comprising folding each sheet upon itself at least once.

25. The process of claim 18 further comprising cutting the ribbon stack to form a plurality of clips of fan folded material.

30

26. The process of claim 18 wherein cutting the ribbon stack occurs in the cross machine direction.

35 27. A dispensing system for fan folded material comprising:  
a dispenser comprising a base and a top enclosing an interior;



a stack of fan folded material stored in the interior, the top comprising an opening through which the fan folded material can pass to an external position outside the dispenser;

the stack of fan folded material comprising:

- 5                   at least two clips of fan folded material;  
                  each clip comprising a plurality of fan folded sheets, each sheet joined to at least one adjacent sheet by a weakened line; and  
                  each clip joined to an adjacent clip by a last sheet of one clip being separably joined to a first sheet of a succeeding clip.

10

28. The system of claim 27 wherein the opening is formed of a yieldable and pass through resistive material which yieldably and resistively allows sheets of the fan folded material to move from the interior of the dispenser to the external position.

- 15   29. The system of claim 27 wherein the top includes a flexible, rubber-like material, and the opening is formed in the flexible, rubber-like material.

30. The system of claim 27 wherein withdrawal of a sheet through the opening pulls a subsequent adjacent sheet through the opening and the sheet is separable from the  
20   adjacent sheet after at least a portion of the adjacent sheet passes through the opening.

31. The system of claim 27 wherein the weakened line comprises perforations.

32. The system of claim 27 wherein the weakened line is formed in a machine direction  
25   of the sheets.

33. The system of claim 27 wherein the plurality of fan folded sheets comprise fold lines formed in a machine direction of the sheets.

- 30   34. The system of claim 27 wherein separably joined comprises adhesively joined.

35. The system of claim 27 further comprising a liquid in combination with the stack of fan folded material, the liquid at an add-on rate of about 25 to about 600 weight percent based on a dry weight of the stack of fan folded material.

35

36. The system of claim 27 wherein each sheet is folded at least once upon itself.

37. A dispensing system for fan folded material comprising:  
a dispenser comprising a base and a top enclosing an interior;  
a stack of fan folded material stored in the interior, the top comprising an opening  
5 through which the fan folded material can pass to an external position outside the dispenser;  
the stack of fan folded material comprising:  
at least two clips of fan folded material;  
each clip comprising a plurality of fan folded sheets, each sheet joined to at  
10 least one adjacent sheet by a weakened line; and  
each clip joined to an adjacent clip by a sheet of one clip being separably joined to a different sheet of a succeeding clip.
38. The system of claim 37 wherein withdrawal of a sheet through the opening pulls a  
15 subsequent adjacent sheet through the opening and the sheet is separable from the adjacent sheet after at least a portion of the adjacent sheet passes through the opening.
39. The system of claim 37 wherein the weakened line comprises perforations.
- 20 40. The system of claim 37 wherein the weakened line is formed in a machine direction of the sheets.
41. The system of claim 37 wherein the plurality of fan folded sheets comprise fold lines formed in a machine direction of the sheets.
- 25 42. The system of claim 37 wherein separably joined comprises adhesively joined.
43. The system of claim 37 further comprising a liquid in combination with the stack of fan folded material, the liquid at an add-on rate of about 25 to about 600 weight percent  
30 based on a dry weight of the stack of fan folded material.
44. A process for dispensing a stack of fan folded material from a dispenser comprising:  
pulling a first sheet of the material through an opening of the dispenser;  
separating the first sheet from a subsequent adjacent second sheet of the material  
35 at a weakened line between the first and second sheets;

pulling a subsequent third sheet of the material through the opening of the dispenser; and

separating the subsequent third sheet of the material from a subsequent adjacent fourth sheet of the material at a separably joined interface between the third and fourth sheets wherein the separably joined interface between the third and fourth sheets is a different type of separably joined interface from the weakened line between the first and second sheets.

45. The process of claim 44 wherein the material comprises wet wipes and the separating the first sheet step and the separating the subsequent third sheet step comprise using a normalized dispensing force in the range of about 3.2 g/cm to about 37.3 g/cm.

46. The process of claim 44 wherein the material comprises wet wipes and the separating the first sheet step and the separating the subsequent third sheet step comprise using a normalized dispensing force in the range of about 5.3 g/cm to about 32 g/cm.

47. The process of claim 44 wherein the material comprises wet wipes and the separating the first sheet step and the separating the subsequent third sheet step comprise using a normalized dispensing force in the range of about 8.0 g/cm to about 26.7 g/cm.

48. The process of claim 44 wherein the material comprises wet wipes and the separating the first sheet step and the separating the subsequent third sheet step comprise using a normalized dispensing force in the range of about 10.7 g/cm to about 21.3 g/cm.

49. The process of claim 44 comprising using a dispensing force which may differ between the separating steps by no more than about 35%.

50. The process of claim 44 comprising using a dispensing force which may differ between the separating steps by no more than about 20%.


51. The process of claim 44 comprising using a dispensing force which may differ between the separating steps by no more than about 10%.


52. The process of claim 44 comprising using a dispensing force which may differ between the separating steps by no more than about 0%.
- 5 53. The process of claim 44 wherein separating the first sheet step comprises tearing perforations at the weakened line between the first and second sheets.
54. The process of claim 44 wherein separating the first sheet step comprises separating along a machine direction of the sheet at the weakened line.
- 10 55. The process of claim 44 wherein all the pulling and separating steps comprise pulling and separating sheets wetted with a liquid at an add-on rate of about 25 to about 600 weight percent based on a dry weight of the stack of fan folded material.
- 15 56. A process for dispensing a stack of fan folded material from a dispenser comprising:  
pulling a first sheet of the material through an opening of the dispenser;  
separating the first sheet from a subsequent adjacent second sheet of the material at a first type of separably joined interface between the first and second sheets;  
pulling a subsequent third sheet of the material through the opening of the  
20 dispenser; and  
separating the subsequent third sheet of the material from a subsequent adjacent fourth sheet of the material at a second type of separably joined interface between the third and fourth sheets wherein the second type of separably joined interface is a different type of separably joined interface from the first type of separably joined interface.
- 25 57. The process of claim 56 wherein the separating the first sheet step comprises separating the first type of separably joined interface at a member from the group consisting of perforations and adhesive.
- 30 58. The process of claim 56 further comprising forming the first type of separably joined interface in a machine direction of the sheets.
59. The process of claim 56 further comprising forming fold lines in the plurality of fan folded sheets in a machine direction of the sheets.

35

60. The process of claim 56 further comprising adding a liquid in combination with the stack of fan folded material, the liquid at an add-on rate of about 25 to about 600 weight percent based on a dry weight of the stack of fan folded material.

5



**FIG. 1A**






FIG. 2



**FIG. 2A**

**FIG. 2B**




FIG. 3A




FIG. 4A




FIG. 3




FIG. 4




FIG. 3C




FIG. 3B




FIG. 5A






FIG. 5



**FIG. 6B**



**FIG. 6A**

**FIG. 6**




FIG. 7A

FIG. 7




FIG. 8A

FIG. 8






FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14B




FIG. 15B




FIG. 14A




FIG. 15A




FIG. 16




FIG. 17




FIG. 18



## INTERNATIONAL SEARCH REPORT

Internat Application No  
PCT/US 02/16996

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 A47K10/42 B65H45/22

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 A47K B65H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, EPO-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 520 308 A (BERG JR CHARLES J ET AL) 28 May 1996 (1996-05-28)	1, 2, 5, 6, 27-31, 34-39, 42-44, 56, 57, 60
A	column 3, line 57 - column 4, line 20  column 5, line 41 - line 64 column 7, line 5 - line 32 column 7, line 61 - line 67; figures ----- -/--	7, 9, 10, 14-16, 18, 22-24

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*Z\* document member of the same patent family

Date of the actual completion of the international search

1 October 2002

Date of mailing of the international search report

09/10/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Porwoll, H

## INTERNATIONAL SEARCH REPORT

Internat Application No  
PCT/US 02/16996

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 00 65972 A (KLEIN KENNETH S) 9 November 2000 (2000-11-09)	1,2,5,6, 27-31, 34-39, 42-44, 56,57,60
A	page 4, line 1 - line 10; figure 4	7-11,15, 16,18,19
A	US 5 033 620 A (DE LUCA RAYMOND F) 23 July 1991 (1991-07-23)	

## INTERNATIONAL SEARCH REPORT

Information on patent family members

Internat Application No

PCT/US 02/16996

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5520308	A	28-05-1996	AT 181891 T	15-07-1999
			AU 4408096 A	17-06-1996
			CA 2204896 A1	30-05-1996
			DE 69510689 D1	12-08-1999
			DE 69510689 T2	30-12-1999
			EP 0793607 A1	10-09-1997
			ES 2133842 T3	16-09-1999
			JP 10509122 T	08-09-1998
			KR 231317 B1	15-11-1999
			WO 9615960 A1	30-05-1996
WO 0065972	A	09-11-2000	AU 4491000 A	17-11-2000
			WO 0065972 A1	09-11-2000
US 5033620	A	23-07-1991	AU 5341590 A	16-11-1990
			CA 2012932 A1	18-10-1990
			EP 0468977 A1	05-02-1992
			JP 4504806 T	27-08-1992
			PT 93786 A	29-11-1991
			WO 9012531 A1	01-11-1990

